

# Centricrete UF

## Rigid Binding Cement Suspension

### Product Properties

- Low-viscosity cement suspension
- Long pot life
- No change in volume during setting
- Restores alkalinity

### Areas of Application

- Rigid filling of cracks, joints and voids in building construction and civil engineering under dry, damp and water-bearing conditions

### Application

#### Preparation

Before injection is carried out, the structure's cracks and voids, respectively the leakage, have to be inspected according to technical standards and regulations, and an injection proposal is to be prepared.

#### Mixing

Centricrete UF consists of two components, component A (binder with additives), component B (Centricrete UF Additive) and water. These components must be mixed in a fast rotating mixer until homogenous.

A forced action mixer should be used for mixing. To achieve an optimal cement suspension the mixing should take at least 10 minutes.

The standard pack (25.03 kg binding agent) allows the production of 41.03 kg  $\approx$  24 l suspension for injection.

The pot life depends on the amount of mixed material and the surrounding temperature conditions present.

#### Injection

Centricrete UF should be injected with an injection-pump MC-I 910 (one-component pump).

For the injection MC-Schlagpacker are recommended.

Work must be stopped at temperatures below + 5 °C.

#### Cleaning

Within the pot life all equipment may be cleaned with water. Partially or completely cured material can only be removed mechanically.



## Technical Data for Centricrete UF

Characteristic	Unit	Value	Comments
Density	g/cm <sup>3</sup>	1.7	ZTV-RISS 93, TP FG-ZL/ZS
Grinding fineness	cm <sup>2</sup> /g	approx. 16,000	DIN EN 196 T6
Pouring time (viscosity)	seconds	approx. 50	DIN EN ISO 9514
Mixing ratio	p. b. w.	25.03:2.35:13.65	comp. A : comp. B : water
Pot life	minutes	approx. 60	at 20 °C and 50 % relative humidity subject to permanent stirring or pumping
Min. application temperature	°C	+ 5	air, substrate and material temperature
Compressive strength	N/mm <sup>2</sup>	28 (after 2 days) 34 (after 7 days) 42 (after 28 days)	DIN EN 196 T1 at 20 °C and 50 % relative humidity
Flexural strength	N/mm <sup>2</sup>	4.0 (after 2 days) 7.0 (after 7 days) 7.2 (after 28 days)	DIN EN 196 T1 at 20 °C and 50 % relative humidity
Change in volume	%	approx. + 2	DIN EN 445 at 20 °C and 50 % relative humidity

## Product Characteristics for Centricrete UF

Colour	grey
Cleaning agent	water
Delivery	25.03 kg Centricrete UF 2.35 kg Centricrete UF Additive
Storage	Can be stored in original sealed packages at temperatures between + 5 °C and + 25 °C in dry conditions for at least 1 year. The same requirements are valid for transport.
Disposal	Packs must be emptied completely.

### Safety Advice

Please take notice of the safety information and advice given on the packaging labels and safety information sheets. GISCODE: ZP1/ZP1 liquid

**Note:** The information on this data sheet is based on our experiences and correct to the best of our knowledge. It is, however, not binding. It has to be adjusted to the individual structure, application purpose and especially to local conditions. Our data refers to the accepted engineering rules, which have to be observed during application. This provided we are liable for the correctness of this data within the scope of our terms and conditions of sale-delivery-and-service. Recommendations of our employees which differ from the data contained in our information sheets are only binding if given in written form. The accepted engineering rules must be observed at all times.

Edition 07/09. Some technical changes have been made to this print medium. Older editions are invalid and may not be used anymore. If a technically revised new edition is issued, this edition becomes invalid.