

# Nafufill GTS

## One-component, polymer-modified dry sprayed mortar (SPCC)

### Product Properties

- Highly resistant to carbonation and de-icing salt
- Low shrinkage, low E-modulus, chloride-proof
- Fast strength build-up, very good adhesion to concrete
- Very good overworking properties, can be overcoated immediately after the surface is finished
- Tested and certified according to ZTV-ING, part 3, paragraph 4
- Non-flammable according to DIN 4102-1 – Material Class A1
- Class R4 according to EN 1504 part 3

### Areas of Application

- Concrete replacement (SPCC) for areas of application in accordance with ZTV-ING, vertical and overhead areas
- Concrete replacement (SPCC) for areas of application in accordance with ZTV-W LB 219 for exposition classes XC 1-4, XD 1-3, XF 1-4, XS 1-3 and XW 1-2
- Concrete replacement for concrete components in contact with groundwater and soil
- Not suitable for lightweight concrete
- Principle 3, 4 and 7; procedure 3.3, 4.4, 7.1 and 7.2 (EN 1504-9)

### Application

#### Substrate Preparation

See leaflet “General Application Advice for Coarse Mortars/Concrete Replacement Systems”.

#### Reinforced Steel

See leaflet “General Application Advice for Coarse Mortars/Concrete Replacement Systems”. Colusal MK should be used as corrosion protection coat. If the mortar is applied in a layer thickness > 40 mm, the reinforcement does not have to be coated.

#### Pre-wetting

Before Nafufill GTS is applied the substrate must be pre-wetted thoroughly. If the concrete parts are completely dried out, the pre-wetting should start one day before application. There should be no standing water on the surface. When beginning to apply the surface should be slightly damp, but not saturated with water.

#### Application/Spraying

The water intake of the nozzle mixing machine should be adjusted to create a homogenous and dust-free spray-mortar. The spray angle between spray-nozzle and ground should be exactly 90° and the distance between ground and nozzle at least 0.5 meters. When spraying behind reinforce-

ments, the angle and distance may be adjusted as necessary. Nafufill GTS can be applied in one or more layers. The interval between individual work steps should be at least 1 hour. The freshly sprayed surface can be left rough as sprayed or levelled with a trowel. It is not allowed to finish Nafufill GTS after it has begun to set. If it is used in the areas of BMV, the application advice in the General Building Supervision Test Certificate are to be observed.

#### General Information

For information on equipment technology, compressor, rebound, supportive casing and application conditions, see leaflet “General Application Advice for Coarse Mortars/Concrete Replacement Systems”.

#### Curing

Nafufill GTS must be prevented from drying out too rapidly and protected from direct sunlight and wind. Curing generally takes 3 days.

#### External Quality Control

University of Dortmund; Faculty for Civil Engineering.

## Technical Data for Nafufill GTS

Characteristic	Unit	Value*	Comments
Largest aggregate	mm	4	-
Fresh mortar density	kg/dm <sup>3</sup>	2.15	-
Dry mortar density	kg/dm <sup>3</sup>	2.01	-
Bending tensile/ compressive strength	MPa	7.1/49.0 9.5/57.8 10.0/62.0	after 7 days after 28 days after 90 days
Dynamic E-modulus	MPa	30,500	after 28 days
Static E-modulus	MPa	24,000	after 28 days
Shrinkage	mm/m	0.75	after 90 days
Carbonisation depth	mm	0	after 90 days
Coverage (dry mortar)	kg/m <sup>2</sup> /mm	2.00	+ rebound
Curing time	minutes	20 - 30	at + 20 °C
Layer thickness	mm	10 25 50 80	minimum layer thickness per work step maximum layer thickness per work step maximum total layer thickness partial application
Application conditions	°C	≥ 5 - ≤ 30	air, material and substrate temperature

## Product Characteristics for Nafufill GTS

Colour	cement-grey
Delivery	25 kg bags, silo material up to 18 t
Storage	Can be stored in cool (below 20 °C) and dry conditions for at least one year in original unopened packs. Protect from frost!
Disposal	Packs must be emptied completely.

For application please note the information in the General Building Supervision Test Certificate.

\*All values have been determined at 23 °C and 50 % relative humidity

### Safety Advice

Please take notice of the safety information and advice given on the packaging labels and safety information sheets.

**Note:** The information on this data sheet is based on our experiences and correct to the best of our knowledge. It is, however, not binding. It has to be adjusted to the individual structure, application purpose and especially to local conditions. Our data refers to the accepted engineering rules, which have to be observed during application. This provided we are liable for the correctness of this data within the scope of our terms and conditions of sale-delivery-and-service. Recommendations of our employees which differ from the data contained in our information sheets are only binding if given in written form. The accepted engineering rules must be observed at all times.

Edition 07/09. Some technical changes have been made to this print medium. Older editions are invalid and may not be used anymore. If a technically revised new edition is issued, this edition becomes invalid.